

Attorney's Docket: 2001US405  
Serial No.: 10/002,710  
Group: 1615

### Amendments to the Specification

Please amend Example 6 beginning on page 27 as follows:

#### Example 6: Waterproof Sunscreen Spray Mist

Ingredients	%w/w	Trade name	Supplier
Phase A			
Anhydrous Ethanol SDA 3A	64.20	SDA 3A	Various
Deionized Water	Q.S.	N/A	N/A
Acrylates/Octylacrylamide	1.00	Dermacryl 79 LT	Natl. Starch
Phase B			
Octyl Methoxycinnamate	7.50	Parsol MCX	Roche
Benzophenone-3	3.00	Escalol 567	ISP
Methyl Anthranilate	3.50	Dermablock	Alzo
Caprylyl Methicone <del>Trimethicone</del>	5.00	SilCare 31M50	Clariant
(C <sub>12</sub> -C <sub>15</sub> )-Alkylbenzoate	10.00	Finsolv TN	Finetex
Butylated hydroxytoluene	0.02	BHT	Clariant
Propylparaben	0.10	Nipasol	Clariant
Vitamin E	0.25	Vitamin E	Protameen
Phase C			
Fragrance	0.50		

#### Manufacturing Procedure:

1. Mix water and ethanol. Disperse slowly Dermacryl. Mix to clarity.
2. Add one by one ingredients of Phase B, mix until clear.
3. Add fragrance. Mix until clear.

Attorney's Docket: 2001US405  
Serial No.: 10/002,710  
Group: 1615

Please amend Example 7, on page 28 as follows:

Example 7: Antiperspirant Cream

Ingredients	%w/w	Trade name	Supplier
Phase A			
Cetyl alcohol	2.5	Crodacol C-95	Croda
Stearyl alcohol	2.5	Crodacol S-95	Croda
Aluminium Chlorohydrate	10.0	Locron P	Clariant
Oleth-10 and Oleth-5	3.0	Emulgin M8	Sidobre Sinnova
Phase B			
Cyclomethicone	9.0	Belsil CM 040	Wacker
Caprylyl Methicone <del>Trimethicone</del>	3.0	SilCare 31M50	Clariant
Deionized Water	63.4	N/A	N/A
Fragrance	q.s.		
Pigments	q.s.		

Manufacturing Procedure:

1. Mix A and heat to 70°C
2. Heat water to 70°C and add to A
3. Add silicones
4. Add fragrance and pigments